

# Primer for Fluoroelastomer Coating

## DAI-EL LATEX GLP-103SR

 TECHNICAL  
DATASHEET

Solvent-based primer for DAI-EL LATEX topcoat.

### Introduction

- DAI-EL LATEX GLP-103SR is a solvent-based primer for DAI-EL LATEX topcoat.
- It makes a clear primer layer displaying excellent adhesion to silicone elastomer substrate.

### Characteristics

Active ingredient [%]	Drying temperature [°C]	Applicable material	Characteristics	Processing method
15	100~150	silicone rubber	Solvent-based (mainly consist of toluene)	Dipping or Spraying

### Characteristics of the coating film

Items	Unit	Data	Reference
Adhesion to silicone rubber	kN/m	0.5	Without primer 0.1

※Processing condition : Primer · 10 min at 60 to 80°C, DAI-EL LATEX · 10 min at 280°C

※As there may be cases of ineffective adhesion due to specific types and compositions of synthetic rubber, please conduct tests beforehand.

\* The numeric values above are typical and not guaranteed.

### Handling method/Safety information

- Be sure to read the notes on SDS and labels before use.
- This product is intended for general industry, and therefore its adequacy and safety as a raw material for medical purposes cannot be guaranteed.

For more information, visit our website.

**DAIKIN INDUSTRIES, LTD.**

<https://www.daikinchemicals.com/>

tds-glp-103sr-E\_ver01\_Mar\_2018  
Copyright (C) DAIKIN INDUSTRIES, LTD., 2018



| Positively Innovative