

1. Introduction

1.1 Product features

- ◇ Special high-strength fluoro resin to obtain a brilliant abrasion resistance.
- ◇ Special binder to gain an excellent high-temperature scratch resistance.
- ◇ Special high-adhesive binder in primer to gain a better adhesion with workpiece.
- ◇ High-hardness pigment combined with special fluoro resin to improve film hardness.

1.2 Main applications

The film obtained can be widely used for ordinary kitchen utensils and household appliance. For example, rice cookers, grills, microwave oven, irons and so on.

The highest temperature for continuous use is 260°C.

1.3 Packaging unit

5kg, 18kg

2. Physical properties

Item	Primer	Middle	Top	Comments
	EZ-1909S-927L	EZ-3718M-5203	EZ-3718M-5003	
Appearance	Black liquid	Metallic Gray liquid	Metallic Light Gray liquid	Visual inspection
Solid content (mass%)	34.5~40.5	45.0~49.0	44.0~48.0	230°C×30min→ 380°C×30min
Viscosity (cP)	250.0~350.0	250.0~400.0	200.0~400.0	Rotating viscosimeter
pH	7.0~10.0	8.0~10.0	8.0~10.0	pH meter
Shelf life	6months	6months	6months	—

- ◆ Test values, not specifications.

3. Processing technique

- ◇ **Please operate the whole process using clean compressed air in tidy environment, because the dusts in atmosphere and the oil and water in compressed air will result in small dots or rusty spots.**
- ◇ **Preheat the workpiece in proper conditions to avoid dewing when the workpiece is too cold or the humidity is too high.**
- ◇ **The temperatures mentioned below represent bulk temperature.**

3.1 Pretreatment of workpiece

3.1.1 Degreasing

Degrease the surface of workpiece using baking or degreasing solvent to clean oil and dusts.

Baking workpiece 10min above 380°C is recommended and the specific conditions depend on workpiece and request of guests.

3.1.2 Surface roughening

Sandblast the surface to a consistent 2.0~3.5 μm roughness (Ra value) using 60#~100# alumina sand emery in case of aluminum workpiece. Then clean the surface by air blow.

3.2 Pretreatment of coating

The coating must be dispersed at 30~50rpm for 30~50min, and filtered by filter screen of 100~200 mesh, 200 mesh is recommended for primer, and 150 mesh for middle coat and top coat.

The coating must be sprayed immediately after thoroughly dispersion.

3.3 Preheating of the substrate material

It is necessary to preheat the substrate material at about 40°C before spraying. Suggest spray the coat when the temperature of the substrate is between 15~35°C.

3.4 Spray of primer

Spray EZ-1909S-927L to the thickness of $13\pm 2\mu\text{m}$. Too thin film thickness will result in poor adhesion. Too thick film thickness will cause mud cracks. The atomizing pressure is 0.2~0.3Mpa when spraying.

3.5 Drying of primer

Dry the primer at 120~150°C for 10~15min as soon as possible after spraying. If drying is not enough coated film may have poor corrosion resistance, bubbling or abnormal appearance.

3.6 Spray of middle coat

After the primer has been dried and cooled to the room temperature, spray the middle coat EZ-3718M-5203 immediately to the thickness of $18\pm 2\mu\text{m}$. The atomizing pressure is 0.2~0.3MPa when spraying.

3.7 Spray of top coat

After spray middle coat, spray the top coat EZ-3718M-5003 immediately to the thickness of $13\pm 2\mu\text{m}$. The atomizing pressure is 0.2~0.3MPa when spraying.

3.8 Drying and sintering of dot coat and top coat

Dry the top coat at 120~150°C for 10~15min as soon as possible after spraying, then sintering at 380°C for 15~20min.

- ◆ Attention: Total dry film thickness should be controlled in 38-50 μm .
- ◆ Attention: The temperature mentioned above is the temperature of the substrate.

4. Precautions in handling

4.1 Ordinary handling

- ◆ The working area should be adequately ventilated at all times. Local ventilation is necessary in the heating process (drying and sintering over 100°C), because the containing surfactants begin to be decomposed by heat higher than approximate 200°C.
- ◆ Maintain equipment regularly (cleaning and exchange) because the decomposed material will accumulate in oven or exhaust duct which is flammable.
- ◆ Put goggles and gloves for protection while handling.
- ◆ Smoking should be prohibited in working area, since smoking tobacco contaminated by fluoro polymer may result in inhalation of decomposed gas. Do not bring tobacco in the working area.
- ◆ Wash hands and face well after handling.
- ◆ Store in a cool and dry place (5~30°C). The case higher than 30°C must be avoided because coagulation and

precipitation will occur. And avoid freezing under 5°C, this product cannot be used after being frozen.

- ◆ Roll the container once a week in order to keep product from coagulating.

Rolling condition: 30~50rpm×30~50min

4.2 Storing conditions

- ◆ Keep containers tightly sealed
- ◆ Keep away from direct sunlight.
- ◆ Be careful to avoid freezing during winter.

4.3 Disposal

Do not release coating into waste water systems. Place it in specially designated container for disposal. Add a coagulation agent (such as nitric acid) to separate the mixture into resin and water, and dispose of the resin portion only through a licensed industrial waste disposal company.

5. Handling emergencies

5.1 IF IN EYES: Rinse cautiously with water for 15 minutes. Remove contact lenses, if present and easy to do. Continue rinsing. If eye irritation persists: Get medical advice/attention.

5.2 IF ON SKIN: Wash with plenty of water and soap thoroughly. If skin irritation occurs: Get medical advice/attention.

5.3 If INHALATION (spray mist or gases from the sintering oven): Move the operator immediately to fresh air, and then seek medical advice.

6. Disclaimer

- ◆ The product is for the industrial use only. We do not guarantee the safety in case the product is used for the other purposes. When using the product for health-care application or food/feed contact application, consult us in advance. This information is based on our present knowledge. However, this shall not constitute a guarantee for any specific product features and shall not establish a legally valid contractual relationship.
- ◆ This data sheet contains the best and latest of our knowledge on the data of issue on laboratory testing and practical application experience, and subject to change without notice. Since the paints are used under unexpected circumstances in some cases, guarantee can not be given except on the quality of those paints themselves.