

# Fluoropolymer NEOFLON PFA AP-230

 TECHNICAL  
DATASHEET

**NEOFLON PFA AP-230 is a fluoro resin that is excellent in melt flowability. It is suitable for extrusion molding.**

## Introduction

- **AP-230** is a copolymer of tetrafluoroethylene and perfluoroalkyl vinyl ether.
- **Good melt flowability** while maintaining excellent properties of PTFE. It can be melt-molded as a thermoplastic resin by **extrusion molding, transfer molding, compression molding** and the like.
- It has been used for **tubes, pipes, sheets, lining applications**.
- It is widely used as a **thick plate** material by compression molding.
- **Excellent chemical resistance** which is not affected by most of the chemicals.
- It retains flexibility without losing toughness under the environment from cryogenic to high temperature.
- Excellent heat resistance. Continuous use temperature is 260 °C.
- **Low dielectric constant and dielectric loss tangent** in a wide range of temperature and frequency.
- It shows high electrical resistance and dielectric strength.
- **Nonflammable** like POLYFLON PTFE and NEOFLON FEP.
- **Excellent weather resistance**. No properties change even when exposed outside for a long time.
- Non-stickiness. It shows excellent releasability and water repellency / oil repellency.

## General physical properties

| Item             | Unit    | Value | Test Method           |
|------------------|---------|-------|-----------------------|
| MFR              | g/10min | 2.0   | 372°C、5kgf            |
| Melting Point    | °C      | 307   | DSC                   |
| Specific Gravity | -       | 2.14  | ASTM D 792 Compliant  |
| Tensile Strength | MPa     | 35    | ASTM D 1708 Compliant |
| Elongation       | %       | 380   | ASTM D 1708 Compliant |

\* The above values are representative values, not guaranteed values.

## Handling method / Safety information

- Be sure to read the notes on SDS and labels before use.
- This product is intended for general industry, and therefore its adequacy and safety as a raw material for medical purposes cannot be guaranteed.

### Packing specification

- 25Kg

---

For more information, visit our website.

**DAIKIN INDUSTRIES, LTD.**

<https://www.daikinchemicals.com/>

tds-ap-230-E\_ver01\_Mar\_2018  
Copyright (C) DAIKIN INDUSTRIES, LTD., 2018